




**C055137A2**

110 Delta Drive  
 Pittsburgh, PA 15238  
 NAFTA Sales: (1)800-245-3984  
 HK Sales : (852)3102-9337  
 magnetics@spang.com  
 www.mag-inc.com



MPP Permeability ( $\mu$ )	$A_L$ (nH/T <sup>2</sup> )	Core Marking			Coating Color
		Lot Number	Part Number	Inductance Grade	
200	42 ± 8%	N/A	N/A	N/A	Gray

Dimensions	Uncoated		Coated Limits			Packaging
	(mm)	(in)	(mm)	(in)		
OD (A)	3.56	0.140	4.19	0.165	max	Bulk Pack 5 vials/box Box Qty= 7500 pcs
ID (B)	1.78	0.070	1.27	0.050	min	
HT (C)	1.52	0.060	2.16	0.085	max	

Electrical Characteristics			Physical Characteristics						
Watt Loss @ 100 kHz, 100mT max(mW/cm <sup>3</sup> )	DC Bias min (A-T/cm)		Voltage Breakdown wire to wire min (V <sub>AC</sub> )	Break Strength min (kg)	Window Area W <sub>A</sub> (mm <sup>2</sup> )	Cross Section A <sub>e</sub> (mm <sup>2</sup> )	Path Length L <sub>e</sub> (mm)	Volume V <sub>e</sub> (mm <sup>3</sup> )	Weight (g)
	80%	50%							
1050	15.0	28.0	*-	1.0	1.27	1.30	8.06	10.5	0.0968

Winding Information					Temperature Rating	
Winding Length Per Turn				Wound Coil Dimensions (mm)		Curie Temp: 460°C
Winding Factor	(mm)	Winding Factor	(mm)	40% Winding Factor		Coating Temp (Continuous up to): 200°C
				OD	4.30	Notes:
				HT	2.56	
				Completely Full Window		Max OD
0%	7.24	40%	7.89	Max HT	2.74	
20%	7.56	45%	7.98	Surface Area (mm <sup>2</sup> )		
25%	7.65	50%	8.08	Unwound Core		60
30%	7.70	60%	8.27	40% Winding Factor		70
35%	7.81	70%	8.48			

### Typical DC Bias Performance

